

FibroSil

Coating-fleece for reworking cracks in render/plaster – texture levelling. Fibre-reinforced crack primer for exterior use, diffusion-open. Recoatable with emulsion paints and silicone resin emulsion paints.



Product Description

Field of Application

FibroSil is a crack-filling coating material. Suitable for reworking render/plaster surfaces and existing, sound emulsion coatings. FibroSil can be coated with emulsion paints, e.g. Amphisil or with silicone resin paints, e.g. AmphiSilan, ThermoSan, PermaSilan or Muresko SilaCryl.

Material Properties

- Crack filling as per BFS Data Sheet No. 19.
- Surface levelling.
- Adhesion promoting on even/smooth surfaces.
- Easy to apply.
- Water-thinnable/-dilutable, low odour.

Material Base / Vehicle

Synthetic resin dispersion (emulsion) according to German standard DIN 55945, fibre-reinforced.

Packaging/Package Size

25 kg

Colours

White.

FibroSil can be tinted to a max. of 5 % with AmphiColor® and CaparolColor colourants. FibroSil is tintable via the ColorExpress tinting & mixing machine system according to all current colour collections in light/bright colours up to luminosity 70 (approx.).

Gloss Level

Matt (flat), G₃

Storage

Keep in a cool, but frost-free place.

Technical Data

Characteristics according to DIN EN 1062: Tinting may cause variations.

- Maximum particle (grit) size: < 1500 µm, S₃
- Density: Approx. 1.45 g/cm³
- Dry film thickness: 200–400 µm, E₄
- Water permeability (w-value): ≤ 0.1 [kg/(m² · h^{0.5})] (low), W₃
- Crack bridging classes: **Surface Coating System:**
1 x 800 g/m² FibroSil (as priming or intermediate coat), class: A1 (> 100 µm)

- Water vapour permeability (sd-value): ≥ 0.14 – < 1.4 m (medium), V₂

- PermaSilan, AmphiSilan, ThermoSan, Muresko SilaCryl, Amphisil

Interior 1	Interior 2	Interior 3	Exterior 1	Exterior 2
–	–	–	+	+

(–) inapplicable / (○) of limited suitability / (+) suitable

Supplementary Product

Suitability according to Technical Information No. 606 Definition of Application Areas



Application

Suitable Substrates	The substrate must be sound/stable, dry, clean, and free from all materials that may prevent good adhesion. In Germany: Follow VOB, Part C, DIN 18363, section 3.
Substrate Preparation	<p>Renders/Plasters in Mortar Groups/Classes PII (Lime-Cement Mortars) and PIII (Cement Mortars) / Minimum Compressive Strength according to DIN EN 998-1: 1.5 N/mm²: New renders/plasters must be left untreated for a sufficiently long time, normally for 2 weeks at 20 °C and 65 % relative humidity. Adverse weather conditions, influenced e.g. by wind or rain, extend the curing process and correspondingly longer holding times must be respected. Existing renders/plasters: Repairs must have adequate time to cure and dry. Apply FibroSil, diluted max. 5 %, on firm render/plaster with normal absorbency. Prime strongly absorbent render/plaster with OptiGrund E.L.F. or CapaSol LF. Prime highly sanding or chalking surfaces with Dupa-grund.</p>
	<p>Concrete: Remove soiling or fines layer mechanically or by high-pressure water jet, in compliance with the regulations. On slightly absorbent or even/smooth surfaces, apply FibroSil diluted max. 5 % with tap (potable) water. Prime highly absorbent surfaces with OptiGrund E.L.F. or CapaSol LF. Prime chalking surfaces with Dupa-grund.</p>
	<p>Sound/Stable Emulsion Paint Coatings: Clean soiled, chalking existing coats by high-pressure water jet, manual washing or other suitable means, in compliance with the regulations. Apply FibroSil thinned max. 5 % with CapaSol LF.</p>
	<p>Stable, Solid Synthetic Resin-Bound (Organic) Renders/Plasters: Clean existing renders/plasters by suitable means. Allow wet cleaned surfaces to dry thoroughly before any further treatment. Apply FibroSil diluted max. 5 % with tap (potable) water.</p>
	<p>Surfaces Infested with Organic Growth (Fungi/Mildew/Mould, Algae): Remove fungal or algal attack by wet blasting, in compliance with the regulations. Then use Capatox or FungiGrund and allow to dry thoroughly.</p>
	<p>Surfaces with Salty Efflorescence: Remove salty efflorescence thoroughly by dry wire brushing and prime with Dupagrund. Coating of such surfaces must be considered a risk for which we cannot accept responsibility, since even after the most thorough treatment the efflorescence may recur.</p>
	<p>Defects: Repair damages up to 20 mm deep with Histolith Renovierspachtel and prime the repaired areas. Interior surfaces: Pre-treat or prime the substrate in accordance with our Technical Information No. 650 "Substrates and their Pre-treatments", depending on substrate requirements.</p>
Method of Application	<p>The product can be applied by paint brush or roller. Spray application is also possible with suitable spray equipment. On smooth surfaces brush application in cross coat technique (crosswise) is recommended, to obtain an even surface texture. Paint rollers should preferably be used on textured substrates, e.g. corrugated renders/plasters (R type). Stir up well before use. Clean tools immediately after use with water.</p>
Surface Coating System	<p>Priming or Intermediate Coat: Apply FibroSil diluted to a max. of 5 % with tap (potable) water. An additional intermediate coat of FibroSil can be applied, if necessary. Finishing Coat: Apply either AmphiSilan, Muresko SilaCryl, Amphisil, PermaSilan or ThermoSan.</p>
Consumption	<p>Approx. 600 – 800 g/m² per coat on an even substrate. On rough-textured surfaces correspondingly more. The exact consumption is best established by a trial coating (test area) on site.</p>
Application Conditions	<p>Lower Temperature Limit for Application and Drying: +5 °C for product, substrate and ambient air.</p>
Drying/Drying Time	<p>At +20 °C and 65 % relative humidity: surface-dry and recoatable after 12 hours. Completely cured and ready for stress after approx. 3 days. Lower temperatures and higher humidity extend the drying time.</p>
Note	<p>Do not apply on sun heated substrates, during strong wind, fog or rain, high relative humidity or imminent rain and frost. Do not apply on horizontal surfaces exposed to rain/water/permanent moisture. Facades in special climatic conditions (high degree of moisture) or subjected to a higher influence of atmospheric exposure: It is recommended to apply our special products, e.g. ThermoSan, Muresko SilaCryl or PermaSilan. These products contain special algicidal and fungicidal agents to delay the forming of organic growth (fungi & algae).</p>

Advice

German Certificates

- FibroSil Prüfzeugnis Schlußanstrich AmphiSilan-Fassadenfarbe Bestimmung der Wasserdampfdiffusionstromdichte und der Wasserdurchlässigkeitsrate
- FibroSil Prüfzeugnis Schlußanstrich Muresko Bestimmung der Wasserdampfdiffusionstromdichte und der Wasserdurchlässigkeitsrate

Please Note (Status as at Date of Publication)

Keep out of reach from children. Use P2 dust filter for grinding. Ensure good ventilation during use and drying. Do not eat, drink or smoke while using the paint. In case of contact with eyes or skin, immediately and thoroughly rinse with water. Do not allow product to enter drains, waterways or soil. Clean utensils immediately after use with soap and water.
When spraying: Do not breathe/inhale spray dust (mist).
Further information: See Material Safety Data Sheet (MSDS).

Disposal

Materials and all related packaging must be disposed of in a safe way in accordance with the full requirements of the local authorities. Particular attention should be made to removing wastage from site in compliance with standard construction site procedures.
In Germany: Only completely emptied containers should be given for recycling. Dispose containers with residues of liquid product via waste collection point accepting old paints and enamels. Dispose dried/hardened product residues as construction site/demolition/municipal or domestic waste.

EU limit value for the VOC content

of this product (Cat. A/a): max. 30 g/l (2010). This product contains max. 30 g/l VOC.

Product Code Paints and Enamels

M-GP01

Substances of Content - Declaration

Polyvinyl acetate resin, titanium dioxide, calcium carbonate, silicates, water, film forming agent, additives, preservative (methylothiazolinone, benzisothiazolinone).

Customer Service Centre

Tel.: +49 6154 71-71710
Fax: +49 6154 71-71711
e-mail: kundenservicecenter@caparol.de

International Distribution: Please see www.caparol.com